APE
best *for* you

# BELVEDERE WHITE 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022847** | 10X30 | 7,30 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 86 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |

apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# MOLDURA BELVEDERE WHITE 5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A023893** | 5X30 | 23,60 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Frost resistance | EN ISO 10545-12 | Not pass the test |

## CHEMICAL PROPERTIES



This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# BELVEDERE WHISPER SAGE 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022853** | 10X30 | 7,80 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 63 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |




This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# MOLDURA BELVEDERE WHISPER SAGE 5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A023895** | 5X30 | 22,10 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Frost resistance | EN ISO 10545-12 | Not pass the test |

## CHEMICAL PROPERTIES

apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# BELVEDERE CEDAR 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022850** | 10X30 | 7,80 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 59 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |




This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# MOLDURA BELVEDERE CEDAR 5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A023894** | 5X30 | 23,00 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Frost resistance | EN ISO 10545-12 | Not pass the test |

## CHEMICAL PROPERTIES



This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# BELVEDERE AVOCADO 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022851** | 10X30 | 6,90 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 58 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |




This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# MOLDURA BELVEDERE AVOCADO

## 5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A023900** | 5X30 | 23,00 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Frost resistance | EN ISO 10545-12 | Not pass the test |

## CHEMICAL PROPERTIES

apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# BELVEDERE TOURMALINE 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022858** | 10X30 | 6,90 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 46 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |


apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# MOLDURA BELVEDERE TOURMALINE 5X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A023896** | 5X30 | 22,10 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Frost resistance | EN ISO 10545-12 | Not pass the test |

## CHEMICAL PROPERTIES

apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.

APE
best *for* you

# BELVEDERE CREAM 10X30

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|---|---|---|---|
| **A022846** | 10X30 | 7,70 | REVESTI |



## DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|---|---|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

## PHYSICAL PROPERTIES

| | | |
|---|---|---|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 23 N/mm$^2$ |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Cracking resistance | EN ISO 10545-11 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |
| Light Reflectance Value (LRV) | | 86 |

## CHEMICAL PROPERTIES

| | | |
|---|---|---|
| Resistance to acids | EN ISO 10545-13 | GLA |
| Resistance to alcalis | EN ISO 10545-13 | GHA |
| Resistance to cleaning products | EN ISO 10545-13 | GA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | GA |
| Stains resistance | EN ISO 10545-14 | 5 |

apegrupo

This document is commercial, with an informative nature relative to tested pieces. It cannot be used in legal or administrative proceedings, nor as an expert opinion or documentary proof. Images are not contractual.